Technical datasheet EN-013

MARCH 2022

Epifanes PU Speedcoat Clear Satin

Two-component PU satin varnish with high end UV filters











PRODUCT DESCRIPTION

This clear satin varnish has a warm satin look, formulated with the latest UV filters. The UV filter protects the wood against discoloration. It can therefore withstand all natural elements even in tropical climates. This varnish has a high scratch resistance and excellent water resistance. Dedicated to spray application with excellent flow and extreme fast overcoating times.

Field of use: Spray only! Suitable on all existent Poly-urethane varnishes regardless of brand. (Note: for faster build up, use Epifanes PP Varnish Extra). Also suited for use as a UV resistant clearcoat over epoxy. This clearcoat will give the same satin look.

PRODUCT INFORMATION

Type Chemical drying

Base Acrylic poly-ol

Gloss Satin (20%)

Colour Transparent

Density at 20°C. 1,041 g/cm³

Viscosity 40 seconds IS0-cup 4 mm

Solids Contents 60 ± 2 vol. %

VOC-level 408 g/l

Packing 2 kg. Component A + 1 kg. Component B. = 3 kg

Shelf life In closed unopened container stored in a dry room at temperatures between 5 - 30°C

Component A 3 years after production date Component B 1 year after production date

Rec. film thickness $60 - 70 \mu \text{m} \text{ wet} = 35 - 40 \mu \text{m} \text{ dry}$

Induction time 20°C. 10 minutes

Thinner spray Epifanes PU Speedcoat Thinner / Epifanes PU Speedcoat Thinner Slow

Thinning in general Thinning ratio depends on product temperature and working area. Avoid overthinning.

	<u> </u>	· · · · · · · · · · · · · · · · · · ·		
Drying times	10°C.	15°C.	20°C.	25°C.
Dust dry	2 hours	1.5 hours	1 hour	1 hour
Recoatable	3 hours	2 hours	1 hour	1 hour
Sandable	48 hours	30 hours	24 hours	20 hours
Potlife after mixing	5 hours	4 hours	3 hours	1.5 hours

The above mentioned drying times are indicative at 65% RAH and 35 µm dry film thickness. Drying also depends on the amount of ventilation and applied wet film thickness. Higher wet film thickness and/or poor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness. Allow each varnish coat sufficient time to dry. Do not apply wet-on-wet!

Substrate Bare wood: Clean with Epifanes Cleaning Solvents and sand with P180. Build up with multi-

ple coats Epifanes PP Varnish. Finish with 3 coats Epifanes PU Speedcoat Satin .

Maintenance of varnish: degreased and sanded P240.

W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 - 360366 info@epifanes.nl www.epifanes.nl



Technical datasheet EN-013

MARCH 2022



Epifanes PU Speedcoat Clear Satin

Two-component PU satin varnish with high end UV filters

APPLICATION

Conditions during application Temperature Relative air humidity minimal 10°C. - maximal 30°C. minimal 50% - maximal 75%

Best results are achieved with a spray gun. We always recommend a RP spray gun, but you can also use a HVLP or Conventional spray gun. Evenly distribute the varnish on the surface. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid large differences in temperature of the product, surface to be varnished and working area. Wet-on-wet application is possible when the solvents have evaporated. When applying another coat after 48 hours, always sand by hand along the wood grain.

Guidelines for spray application:

Thinning volume	Nozzle RP	Pressure	Visco DIN-cup 4 mm
15-20%	1.1 mm - 1.3 mm	2-2.5 Bar	18-20 sec.

SYSTEM BUILD UP

	Step 1	Step 2	Step 3
Product	EPIFANES PP Varnish extra	EPIFANES PP Varnish extra	EPIFANES PU Speedcoat Clear Satin
Numb. of coats	1	At least 3, but the more, the better	3
Thinner	EPIFANES Thinner for PP Varnish	Epifanes Thinner for PP Varnish	EPIFANES PU Speedcoat Spraythinner
Thinning ratio	25%	0-10%	15-20%
Drying time 20°C.	2-3 hours	2-3 hours	1 hour
Sanding grit	Dry P220	No sanding between coats within 48 hours. After 48 hours always sand with P320	No sanding between coats within 48 hours. After 48 hours always sand with P320
Remarks	First penetrating varnish coat. For full varnish penetration into the wood fibers, apply this first coat heavily thinned.	PP Varnish Extra may be thinned with Epifanes PU Brushthinner. This slow evaporating thinner will allow the PP Varnish Extra to flow better.	Sand final coat PP Varnish Extra with P320 before applying the first coat. Between coats only lightly sanding is required.

Theoretical coverage Practicle coverage

15m² per liter @ 40 µm dry film thickness

Dependent on condition of substrate, loss of material due to factors such as applica-

tion technique, shape of object, circumstances during application.

Polishing Not recommended

Recoatbility with other **Epifanes varnishes**

Epifanes Clear Varnish 1-C High gloss alternative **Epifanes Woodfinish Gloss** 1-C High gloss alternative

Epifanes Woodfinish Matte 1-C Matt finish for interior / exterior use

Epifanes Rubbed Effect Varnish 1-C Satin finish for interior use Epifanes Poly-urethane Clear Gloss 2-C Gloss finish with UV Filter Epifanes Poly-urethane Clear Satin 2-C Satin finish with UV Filter

Epifanes PU Speedcoat Clear Gloss 2-C Spray finish for interior / exterior use with UV filter

Safety

The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

Allthough the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties.

THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 – 360366 info@epifanes.nl www.epifanes.nl

