

Product Line Propspeed Etching Primer

Description A two-component etching primer, chemically drying by reaction of the mixed components and providing protection against corrosion and increasing the adhesive property of the subsequent coats.

Typical Uses As a pre-treatment primer on non-ferrous metals such as bronze and aluminium as well as zinc and galvanised iron. May also be used as pre-treatment primer on blast-cleaned steel plates.

Physical Properties

Mixing Ratio	- Base : Additive = 4 : 1 by volume
Colour	- Base : Yellow Additive : Clear
Theoretical Coverage	- 12m ² /L
Dry Film Thickness	- 8 microns
Dry time	- 10 minutes touch dry (temperature dependent) - 1 hour hard dry @ 20°C
Painting Interval	- Apply Propspeed Clear when Etching Primer is just touch dry
Pot Life	- 8 hrs @ 20°C.
Clean up	- Acetone

Application Brush, Airless spray

Surface Preparation & Application

See application video www.propspeed.com

Propellers, shafts and rudders

Clean off all marine growth. Sand with 80 grit paper. Wash with clean water to remove sanding dust and allow to dry. Use Propclean to remove any organic contaminants, including grease and oil resulting from finger tip contact with the metal substrate. Wipe on and wipe off immediately with a clean cloth until clean. Apply Propprep to provide a chemically conditioned surface and wipe off with a clean cloth. Apply 2 coats Propspeed Etching Primer, when touch dry apply 1 full coat Propspeed Clear by brush, ensuring edges are free from drips. Do not immerse for minimum of 8 hours.

New Propellers

We recommend pre-conditioning all metal with Propclean and Propprep before applying the Etch Primer, refer to Propclean and Propprep data sheets.

Removal and Recoating of Propspeed

Process: When reapplying Propspeed the following steps should be taken.

- Remove the old Propspeed using 80 grit paper or Propstrip (refer TDS sheet).
- Clean entire area with Propclean and Propprep.
- Recoat as per Propspeed instructions.

Health & Safety

Clear Coat

Contains organic solvents including xylene. Do not expose to naked flame or high temperature heating equipment. Avoid skin contact. It is recommended that a barrier cream or gloves be used for hands and eye protection is worn. Always ensure adequate ventilation when painting.

Transport

UN No.:	1263
Class:	3a
Hazchem:	2(Y)E
Packing Group	II

Storage

Do not store close to naked flames or near high temperature heating equipment.