

# Microsfere

Code: 6320.005

## HOLLOW GLASS -MICROSPHERES

- SUITABLE TO PRODUCE:
- SELFLEVELLING COMPOUNDS
- FILLING COMPOUNDS
- FILLERS

## CHARACTERISTICS

MICROSFERE belongs to the range of additives to be mixed with RESINA 2000 in order to produce compounds with different properties. MICROSFERE consists of microspheres with low absorbency of humidity, which therefore can be used for applications above and below the waterline. Their main purpose is the production of fillers with low specific gravity, which are easy to sand and whose consistency may be varied according to the needs of the operator. These fillers are best suited for the repair of horizontal cracks, small surface defects and as knifing fillers.

## TECNICAL DATA

Curing mechanism:	/
Specific weight:	/
Solid By Volume:	/
Flash Point:	/
Appearance:	/
Colour:	/
Packaging:	0,75/ 2,50 litres

## SURFACE PREPARATION

Before applying Resina 2000, the surface must be completely dry and clean. Wooden surfaces must be dry and clean, as well as free from grease and oil. The areas to be treated should be sandpapered at first.

## APPLICATION

MICROSFERE shall be added to RESINA 2000 only after component A has been mixed thoroughly with component B with a ratio of 2:1.

### Liquid compound

Mix 2 parts of already catalysed Resina 2000 + 1 part of Microsfere, in order to produce a liquid compound suitable for the repair of horizontal cracks and for gluing.

### Filling compound

Mix 1 part of already catalysed Resina 2000 + 1 part of Microsfere, in order to produce a half-liquid, self-levelling compound suitable as a filling compound for small surface defects and as a knifing filler.

### Filler

Mix 1 part of already catalysed Resina 2000 + 3 parts of Microsfere, in order to produce a filler suitable to be applied at high thickness.

# Microsfere

Code: 6320.005

## HOLLOW GLASS -MICROSPHERES

### APPLICATION DATA

Drying time before use (20 °C): /  
 Pot Life (20 °C): /  
 Application temp. min/ max: +5/+35 °C  
 Hardener: /  
 Mixing ratio by volume: /  
 Mixing ratio by weight: /  
 Thinner/Thinner for cleaning: /  
 Wet film thickness per coat: /  
 Dry film thickness per coat: /  
 Theoretical coverage per coat: /  
 Minimum covering time (20 °C): /  
 Maximum covering time (20 °C): /  
 Number of coats: /

### NOTES


### SAFETY RULES

The product does not contain dangerous components in conformity with the rules of the EEC, should be used with the usual working precautions and not dispersed into the environment. Keep out of reach of children. Before use read the sections 7-8 of the Safety Data Sheet (MSDS).  
**INSTRUCTIONS FOR THE SAFE BIOCIDAL PRODUCT DISPOSAL AND PACKAGING**  
 Empty packaging having contained biocidal products: empty packaging shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre.  
 Packaging containing unused biocidal product: the unused product shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre, in this case it is forbidden to recycle packaging. Do not empty into drains and watercourses. The paint cans must not be stocked outside and must be stored at a temperature between 10 ° C and 35 ° C. Do not expose to the sun.

**DISCLAIMER** The information in this data sheet is based on accurate laboratory tests and practical experience, which guarantee the quality of the product if used according to our recommendations. The data contained herein are liable to modification as a result of continuous product development. We do not accept any liability arising from use not in accordance with our recommendations, unless authorized specifically by the Veneziani Technical Services. This edition annuls and replaces all previous issues.